

The Slip Coefficient test below was completed by Nu-Safe located in Walton Kentucky which shows our Dry COF to be well within the safe range for a Dry floor wax.



COF FLOOR EVALUATION

Client	Red Alert Wax, LLC				Technician:	Ken Fisher, Nu-Safe Floor Solutions			
Location/Address:					Address/Phone No.:	44 Cummings Drive, Walton, KY 41094			
Date/Time of Tests:	8/7/14 12:00 PM				Serial #:				
Test Method:					Test Foot	Leather			
Zone Tested	Foot & Test Type	Surface Slope	Floor Material	Floor Finish	Floor Condition	Wet/Dry	Reading 1 North	Reading 2 East	Average
Tile A	Leather Dry SCOF					Dry	0.85	0.86	0.86
Tile B	Leather Dry SCOF					Dry	0.90	0.95	0.93

Safe 0.50 and above
 0.40-0.49
 Unsafe 0.39 and below

The Slip Coefficient test below was completed by Nu-Safe located in Walton Kentucky which shows our Wet COF to be well within the safe range for a Wet floor wax.



COF FLOOR EVALUATION

Client	Red Alert Wax, LLC				Technician:	Ken Fisher, Nu-Safe Floor Solutions			
Location/Address:					Address/Phone No.:	44 Cummings Drive, Walton, KY 41094			
Date/Time of Tests:	8/7/14 12:00 PM				Serial #:				
Test Method:					Test Foot	Neolite			
Zone Tested	Foot & Test Type	Surface Slope	Floor Material	Floor Finish	Floor Condition	Wet/Dry	Reading 1 North	Reading 2 East	Average
Tile A	Neolite Wet SCOF					Wet	0.70	0.70	0.70
Tile B	Neolite Wet SCOF					Wet	0.83	0.73	0.78

Safe 0.50 and above
 0.40-0.49
 Unsafe 0.39 and below

